

LNP™ LUBRICOMP™ ZX05506 compound

Polyphenylene Ether + PS

SABIC Innovative Plastics

Message:

LNP LUBRICOMP* ZX05506 is a compound based on PPE+PS Blend resin containing 15% Graphite Powder, 20% PTFE. Added feature of this material is: Wear Resistant.
Also known as: LNP* LUBRICOMP* Compound ZML-4334
Product reorder name: ZX05506

General Information			
Additive	Graphite Powder Lubricant (15%)		
	PTFE Lubricant (20%)		
Features	Good Wear Resistance		
	Lubricated		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.35	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			
Flow : 24 hr	0.50	%	ASTM D955, ISO 294-4
Across Flow : 24 hr	0.50	%	ASTM D955
Across Flow : 24 hr	0.54	%	ISO 294-4
Water Absorption (Equilibrium, 23°C, 50% RH)	0.050	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	4900	MPa	ASTM D638
--	4910	MPa	ISO 527-2/1
Tensile Strength			
Break	52.5	MPa	ASTM D638
Break	50.0	MPa	ISO 527-2
Tensile Elongation			
Break	2.4	%	ASTM D638
Break	2.5	%	ISO 527-2
Flexural Modulus			
--	4960	MPa	ASTM D790
--	5370	MPa	ISO 178
Flexural Strength			
--	99.2	MPa	ASTM D790
--	94.7	MPa	ISO 178

Coefficient of Friction			ASTM D3702 Modified
vs. Itself - Dynamic	0.34		
vs. Itself - Static	0.34		
Wear Factor - Washer	174	10 ⁻¹⁰ in ⁵ -min/ft-lb-hr	ASTM D3702 Modified
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	32	J/m	ASTM D256
23°C ²	2.9	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	180	J/m	ASTM D4812
23°C ³	13	kJ/m ²	ISO 180/1U
Instrumented Dart Impact			
23°C, Energy at Peak Load	3.80	J	ASTM D3763
--	1.23	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, Unannealed, 3.20 mm	122	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ⁴	126	°C	ISO 75-2/Af
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	4.0	hr	
Rear Temperature	277 to 288	°C	
Middle Temperature	288 to 299	°C	
Front Temperature	299 to 310	°C	
Processing (Melt) Temp	299 to 304	°C	
Mold Temperature	82.2 to 110	°C	
Back Pressure	0.172 to 0.344	MPa	
Screw Speed	30 to 60	rpm	
NOTE			
1.	50 mm/min		
2.	80*10*4		
3.	80*10*4		
4.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

