

# ColorRx® PCPT-0900CRNB

Polycarbonate + PET  
LTL Color Compounders, Inc.

Message:

A PC/PET alloy with outstanding chemical resistance designed for use in medical equipment enclosures, such as monitoring and imaging devices, where body contact is not an issue.

General Information			
Features	Good Chemical Resistance		
Uses	Medical/Healthcare Applications		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.23	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR)	8.5	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.60 to 0.90	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (3.20 mm)	110		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield	49.3	MPa	
Break	55.5	MPa	
Tensile Elongation			ASTM D638
Yield	4.6	%	
Break	150	%	
Flexural Modulus	2100	MPa	ASTM D790
Flexural Strength	75.8	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	900	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	85.6	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating (1.00 mm)	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: [sales@su-jiao.com](mailto:sales@su-jiao.com)

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

