

# ADENE NCQAGD

Polypropylene Copolymer

A.D. Compound spa

Message:

ADENE NCQAGD is a Polypropylene Copolymer (PP Copolymer) material filled with 40% calcium carbonate. It is available in Europe or North America.  
Primary attribute of ADENE NCQAGD: Copolymer.  
Typical application of ADENE NCQAGD: Appliances

| General Information                               |                                        |          |             |
|---------------------------------------------------|----------------------------------------|----------|-------------|
| Filler / Reinforcement                            | Calcium Carbonate,40% Filler by Weight |          |             |
| Features                                          | Copolymer                              |          |             |
|                                                   | Detergent Resistant                    |          |             |
| Uses                                              | Appliances                             |          |             |
| Appearance                                        | Natural Color                          |          |             |
| Forms                                             | Pellets                                |          |             |
| Physical                                          | Nominal Value                          | Unit     | Test Method |
| Density                                           | 1.24                                   | g/cm³    | ISO 1183    |
| Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)         | 12                                     | g/10 min | ISO 1133    |
| Ash Content                                       | 40                                     | %        | ISO 3451-1  |
| Mechanical                                        | Nominal Value                          | Unit     | Test Method |
| Flexural Modulus                                  | 1900                                   | MPa      | ISO 178     |
| Impact                                            | Nominal Value                          | Unit     | Test Method |
| Notched Izod Impact Strength (23°C)               | 5.0                                    | kJ/m²    | ISO 180/1A  |
| Unnotched Izod Impact Strength (23°C)             | 15                                     | kJ/m²    | ISO 180/1U  |
| Thermal                                           | Nominal Value                          | Unit     | Test Method |
| Heat Deflection Temperature (1.8 MPa, Unannealed) | 52.0                                   | °C       | ISO 75-2/A  |
| Vicat Softening Temperature                       | 90.0                                   | °C       | ISO 306/B   |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT