

SILVER® PC2320.L30

Polycarbonate

Guangdong Silver Age Sci & Tech. Co., Ltd

Message:

SILVER® Polycarbonate is applied to many fields, such as automobiles, office automation equipments, electronics, medical equipments and sports equipments. In addition, the custom—made products should be developed by buyers ‘ requirements in order to meet special usage.

Glass Fiber Reinforced PC

Characteristic:

UL—94V0/1.5mm, excellent toughness, good appearance

Application:

fire fighting facility, relay, connector, switch, plugs, flame resistance film

General Information			
Filler / Reinforcement	Glass Fiber		
Features	Flame Retardant		
	Good Toughness		
	High Rigidity		
Uses	Connectors		
	Film		
	Plugs		
	Switches		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.41	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	9.0	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹	105	MPa	ASTM D638
Tensile Elongation ² (Break)	2.0	%	ASTM D638
Flexural Modulus ³	6800	MPa	ASTM D790
Flexural Strength ⁴	160	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (Area) (23°C)	9.00	kJ/m ²	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	142	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating (1.50 mm)	V-0		UL 94
Injection	Nominal Value	Unit	
Processing (Melt) Temp	270 to 330	°C	
NOTE			

1.	10 mm/min
2.	10 mm/min
3.	5.5 mm/min
4.	5.5 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

