

GERMAMID 6 KSZ

Polyamide 6
Kunststoff-Kontor-Hamburg GmbH

Message:
GERMAMID 6 KSZ is a polyamide 6 (nylon 6) material. This product is available in Europe.

General Information			
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Density	1.10	g/cm ³	ISO 1183
Molding Shrinkage	1.0 - 2.0	%	ISO 294-4
Water Absorption (Saturation, 23°C)	2.2	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2700	MPa	ISO 527-2
Tensile Stress (Yield)	65.0	MPa	ISO 527-2
Tensile Strain (Break)	50	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	13	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength	No Break		ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	180	°C	ISO 75-2/B
Melting Temperature	218	°C	
Thermal Conductivity	0.23	W/m/K	ISO 8302
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+12	ohms	IEC 60093
Additional Information			

Tensile Strain at Break, ISO 527: >50%

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT