

Ferro PP LPP30BA03NA

Polypropylene Copolymer

Ferro Corporation

Message:

Ferro PP LPP30BA03NA is a Polypropylene Copolymer (PP Copolymer) material filled with 32% calcium carbonate. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America for injection molding.

Important attributes of Ferro PP LPP30BA03NA are:

- Copolymer
- Good UV Resistance
- UV Stabilized

General Information			
Filler / Reinforcement	Calcium Carbonate,32% Filler by Weight		
Additive	UV Stabilizer		
Features	Copolymer		
	Good UV Resistance		
Appearance	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.15	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	1.5	g/10 min	ASTM D1238
Molding Shrinkage			ASTM D955
Flow	1.5	%	
Across Flow	1.7	%	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	70		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	22.8	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	150	%	ASTM D638
Flexural Modulus			ASTM D790
1% Secant : 23°C	1680	MPa	
Tangent : 23°C	1920	MPa	
Flexural Strength (23°C)	36.5	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	120	J/m	ASTM D256
Unnotched Izod Impact (23°C)	No Break		ASTM D4812
Gardner Impact (23°C)	26.0	J	ASTM D5420
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648

0.45 MPa, Unannealed	102	°C
1.8 MPa, Unannealed	57.2	°C
Injection	Nominal Value	Unit
Drying Temperature	93.3	°C
Drying Time	2.0 to 3.0	hr
Rear Temperature	202 to 204	°C
Middle Temperature	204 to 210	°C
Front Temperature	210 to 213	°C
Nozzle Temperature	213 to 218	°C
Mold Temperature	43.3 to 51.7	°C
Back Pressure	0.345 to 0.689	MPa

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

