

# Baypreg® F 310 (25 mm Glass Mat Reinforced Sandwich)

Polyurethane  
Covestro - PUR

Message:

Baypreg F 310 system is a two component polyurethane system used in compression molding of fiber-reinforced sandwich panels to produce a variety of automotive parts. Some identified applications include door panels, sunshades, spare tire covers, load floors, etc. The Baypreg F 310 system provides lightweight alternatives to ABS, PP, SMC, and wood products while demonstrating very high flexural stiffness and excellent thermal properties. Baypreg F 310 system offers very diverse properties over a wide range of part thicknesses and densities while still providing cost effective substrate parts when combined with reinforcing materials. As with any product, use of the Baypreg F 310 system in a given application must be tested (including field testing, etc.) in advance by the user to determine suitability.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 50% filler by weight		
Uses	Application in Automobile Field		
Forms	Liquid		
Processing Method	Compression molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.128	g/cm³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus (22°C)	2750	MPa	ASTM D790
Flexural Strength (22°C)	7.00	MPa	ASTM D790
Thermoset	Nominal Value		
Thermoset Components			
Component a	Mixing ratio by weight: 100		
Component B	Mixing ratio by weight: 180		
Additional Information			

Part A  
Type: Isocyanate  
Appearance: Dark Brown Liquid  
Specific Gravity @ 25°C: 1.21  
Viscosity @25°C: 350 mPa  
Flash Point, PMCC: 223°C  
NCO: 28.5 wt%

Part B  
Type: Polyol  
Appearance: Black liquid  
Specific Gravity @ 25°C: 1.083  
Viscosity @25°C: 1380 mPa-s  
Flash Point, PMCC: 166°C  
Hydroxyl Number: 610  
Reinforcing Mat Weight: 600 g/m³Tricel Honeycomb (untreated): 25 mmMolded Thickness: 25 mmChemical Temperature: 21 to 27°C Mold Temperature: 100 to 120°C Cure Time: 65 to 90 sec Time from Spray to Mold Close: 75 sec Nucleation (resin): Up to 40% or as needed Degassing, if necessary: Open tool at 17 sec for 5 sec

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

