

Stylac™ VA58

Acrylonitrile Butadiene Styrene
Asahi Kasei Chemicals Corporation

Message:

Stylac™ VA58 is an Acrylonitrile Butadiene Styrene (ABS) product. It is available in Africa & Middle East, Asia Pacific, or Europe.
Characteristics include:
Flame Rated
Flame Retardant

General Information			
UL YellowCard	E171626-225616		
Additive	Flame Retardant		
Features	Flame Retardant		
	Halogenated		

Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.20	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	25	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (220°C/10.0 kg)	25.0	cm ³ /10min	ISO 1133
Molding Shrinkage - Flow	0.40 to 0.60	%	ASTM D955

Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	46.8	MPa	ISO 527-2/50
Flexural Modulus ¹	2550	MPa	ISO 178
Flexural Stress ²	78.7	MPa	ISO 178

Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	11	kJ/m ²	ISO 179

Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	75.7	°C	ISO 75-2/A
Vicat Softening Temperature	91.5	°C	ISO 306/B
RTI Elec	60.0	°C	UL 746
RTI Imp	60.0	°C	UL 746
RTI Str	60.0	°C	UL 746
Ball Pressure Test ³	80	°C	EMAC

Flammability	Nominal Value	Test Method
Flame Rating	UL 94	
2.10 mm	V-0	
2.50 mm	5VA	

NOTE			
1.	2.0 mm/min		

2.	2.0 mm/min
3.	Registered Number: B-2285

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

