Mapex AN0320SB

Polyamide 6

Ginar Technology Co., LTD.

Message:

Mapex AN0320SB is a polyamide 6 (nylon 6) product, which contains a 15% glass fiber reinforced material. It can be processed by injection molding and is available in North America, Africa and the Middle East, Europe or Asia Pacific. Mapex AN0320SB applications include the automotive industry, consumer goods, handles and sporting goods.

Features include:

Hard

Heat resistance

General Information				
Filler / Reinforcement	Glass fiber reinforced material, 15% filler by weight			
Features	Rigidity, high			
	Heat resistance, high			
Uses	Handle			
	Application in Automobile Field			
	Sporting goods			
	Toys			
Appearance	Black			
Appearance	Particle			
Forms				
Processing Method	Injection molding			
Physical	Nominal Value	Unit	Test Method	
Specific Gravity	1.23	g/cm³	ASTM D792	
Molding Shrinkage - Flow	0.40	%	ASTM D955	
Water Absorption (24 hr)	1.4	%	ASTM D570	
Hardness	Nominal Value	Unit	Test Method	
Rockwell Hardness (R-Scale)	120		ASTM D785	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength	89.6	MPa	ASTM D638	
Tensile Elongation (Break)	2.0	%	ASTM D638	
Flexural Modulus	4310	MPa	ASTM D790	
Flexural Strength	138	MPa	ASTM D790	
Impact	Nominal Value	Unit	Test Method	
Notched Izod Impact	43	J/m	ASTM D256	
Thermal	Nominal Value	Unit	Test Method	
Deflection Temperature Under Load (1.8 MPa, Unannealed)	200	°C	ASTM D648	
Injection	Nominal Value	Unit		
Drying Temperature	90.0	°C		

Drying Time	4.0	hr	
Suggested Max Moisture	0.20	%	
Suggested Shot Size	40 - 80	%	
Rear Temperature	230 - 240	°C	
Middle Temperature	240 - 260	°C	
Nozzle Temperature	230 - 240	°C	
Mold Temperature	60.0 - 80.0	°C	
Back Pressure	0.00 - 0.294	MPa	
Screw Speed	50 - 70	rpm	
Injection instructions			

Injection Pressure: 50 to 70%Injection Speed: 50 to 70%

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

