

Acrigel® AFP100

Polymethyl Methacrylate Acrylic

Unigel Plásticos

Message:

High flow rate, good thermal resistance and good balance stiffness/impact.

Applications:

complex design parts

appliances.

General Information			
Features	Good Impact Resistance		
	Good Stiffness		
	High Flow		
	Medium Heat Resistance		
Uses	Appliances		
	Engineered Applications		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.19	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)	14	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.30 to 0.60	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	93		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	66.0	MPa	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.20 mm)	13	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 3.20 mm)	92.0	°C	ASTM D648
Vicat Softening Temperature			
--	92.0	°C	ASTM D1525 ¹
--	100	°C	ASTM D1525 ²
Optical	Nominal Value	Unit	Test Method
Refractive Index	1.490		ASTM D542
Transmittance	92.0	%	ASTM D1003
Injection	Nominal Value	Unit	
Drying Temperature	85.0	°C	

Drying Time	4.0	hr
Rear Temperature	200	°C
Middle Temperature	210	°C
Front Temperature	220	°C
Nozzle Temperature	215	°C
Mold Temperature	60.0	°C

NOTE

1. Rate A (50°C/h), Loading 2 (50 N)
2. Rate B (120°C/h), Loading 1 (10 N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

