

Durethan® BC 550 Z DUSXBL 900116

Polyamide 6

LANXESS GmbH

Message:

PA 6, non-reinforced, blow molding, improved impact strength, heat-aging stabilized

General Information				
Additive		heat stabilizer		
Features		Impact resistance, good		
		Thermal Stability		
Agency Ratings		EC 1907/2006 (REACH)		
Processing Method		Blow molding		
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.07	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 2577
Vertical flow direction: 260°C, 2.00mm ¹	1.5	--	%	ISO 2577
Vertical flow direction: 120°C, 4 hours, 2.00mm ²	0.20	--	%	ISO 2577
Flow direction: 260°C, 2.00mm ³	1.5	--	%	ISO 2577
Flow direction: 120°C, 4 hours, 2.00mm ⁴	0.20	--	%	ISO 2577
Water Absorption				ISO 62
Saturated, 23°C	9.1	--	%	ISO 62
Equilibrium, 23°C, 50% RH	2.5	--	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	2000	430	MPa	ISO 527-2/1
Tensile Stress (Yield, 23°C)	50.0	--	MPa	ISO 527-2/50
Tensile Strain (Yield, 23°C)	4.0	--	%	ISO 527-2/50
Nominal Tensile Strain at Break (23°C)	140	170	%	ISO 527-2/50
Flexural Modulus ⁵ (23°C)	1800	470	MPa	ISO 178/A
Flexural Stress				ISO 178/A
3.5% strain, 23°C	55.0	14.0	MPa	ISO 178/A
23°C ⁶	66.0	21.0	MPa	ISO 178/A
Flexural Strain at Flexural Strength ⁷ (23°C)	6.0	9.0	%	ISO 178/A
ISO Shortname	PA 6-HI, BHR, 14-020	--		ISO 1874
Residual Moisture Content	0.0 - 0.060		%	Karl Fisher

Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	25	25	kJ/m ²	ISO 179/1eA
23°C	100	130	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	No Break	No Break		ISO 179/1eU
23°C	No Break	No Break		ISO 179/1eU
Notched Izod Impact				ISO 180/1A
-30°C	25	25	kJ/m ²	ISO 180/1A
23°C	85	110	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength				ISO 180/1U
-30°C	No Break	No Break		ISO 180/1U
23°C	No Break	No Break		ISO 180/1U
Multi-Axial Instrumented Impact Energy				ISO 6603-2
-30°C	67.0	--	J	ISO 6603-2
23°C	65.0	--	J	ISO 6603-2
Multi-Axial Instrumented Impact Peak Force				ISO 6603-2
-30°C	5700	--	N	ISO 6603-2
23°C	5000	--	N	ISO 6603-2
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	53.0	--	°C	ISO 75-2/A
Melting Temperature ⁸	219	--	°C	ISO 11357-3
Linear thermal expansion coefficient				ISO 11359-2
Flow: 23 to 55°C	1.4E-4	--	cm/cm/°C	ISO 11359-2
Lateral: 23 to 55°C	1.3E-4	--	cm/cm/°C	ISO 11359-2
Injection	Dry	Unit	Test Method	
Drying Temperature - Dry Air Dryer	80.0		°C	
Drying Time - Dry Air Dryer	2.0 - 6.0		hr	
Processing (Melt) Temp	230 - 280		°C	
Mold Temperature	60.0 - 90.0		°C	
NOTE				
1.	60x60x2mm, 80°C MT, 600 bar			
2.	60x60x2mm			
3.	60x60x2mm, 80°C MT, 600 bar			
4.	60x60x2mm			

5.	2.0 mm/min
6.	2.0 mm/min
7.	2 mm/min
8.	10°C/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

