

LNP™ LUBRICOMP™ WFL36 compound

Polybutylene Terephthalate

SABIC Innovative Plastics

Message:

LNP LUBRICOMP* WFL36 is a compound based on PBT resin containing 30% Glass Fiber, 15% PTFE. Added features of this material include: Wear Resistant.

Also known as: LNP* LUBRICOMP* Compound WFL-4036

Product reorder name: WFL36

General Information			
UL YellowCard	E121562-101282605		
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Additive	PTFE Lubricant (15%)		
Features	Good Wear Resistance		
	Lubricated		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.68	g/cm³	ASTM D792, ISO 1183
Molding Shrinkage			ASTM D955, ISO 294-4
Flow : 24 hr	0.10 to 0.30	%	
Across Flow : 24 hr	0.50 to 1.0	%	
Water Absorption			
24 hr, 50% RH	0.040	%	ASTM D570
Equilibrium, 23°C, 50% RH	0.040	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	10300	MPa	ASTM D638
--	10600	MPa	ISO 527-2/1
Tensile Strength (Break)	118	MPa	ASTM D638, ISO 527-2
Tensile Elongation			
Break	2.3	%	ASTM D638
Break	2.2	%	ISO 527-2
Flexural Modulus			
--	10200	MPa	ASTM D790
--	10000	MPa	ISO 178
Flexural Strength			
--	193	MPa	ASTM D790
--	187	MPa	ISO 178
Coefficient of Friction			ASTM D3702 Modified
vs. Itself - Dynamic	0.57		

vs. Itself - Static	0.41		
Wear Factor - Washer	42.0	10 ⁻¹⁰ in ⁵ -min/ft-lb-hr	ASTM D3702 Modified
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	96	J/m	ASTM D256
23°C ²	9.2	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	680	J/m	ASTM D4812
23°C ³	43	kJ/m ²	ISO 180/1U
Instrumented Dart Impact			
23°C, Energy at Peak Load	13.7	J	ASTM D3763
--	2.61	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, Unannealed, 3.20 mm	218	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ⁴	214	°C	ISO 75-2/Af
CLTE			ASTM E831, ISO 11359-2
Flow : -40 to 40°C	3.9E-5	cm/cm/°C	
Transverse : -40 to 40°C	6.7E-5	cm/cm/°C	
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.050	%	
Rear Temperature	221 to 232	°C	
Middle Temperature	243 to 254	°C	
Front Temperature	260 to 271	°C	
Processing (Melt) Temp	238 to 266	°C	
Mold Temperature	82.2 to 98.9	°C	
Back Pressure	0.172 to 0.344	MPa	
Screw Speed	30 to 60	rpm	
NOTE			
1.	50 mm/min		
2.	80*10*4		
3.	80*10*4		
4.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

