

Badaflex® TPU 85A 8046 EX

Thermoplastic Polyurethane Elastomer

Bada AG

Message:

Badaflex® TPU 85A 8046 EX is a thermoplastic polyurethane elastomer material. This product is available in Europe and is processed by extrusion or injection molding.

General Information			
Processing Method	Extrusion		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.12	g/cm ³	DIN 53479
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	85		DIN 53505
Mechanical	Nominal Value	Unit	Test Method
Abrasion Loss	37.0	mm ³	DIN 53516
Films	Nominal Value	Unit	Test Method
Tensile Strength - MD	35.0	MPa	DIN 53504
Tensile Elongation - MD (Break)	650	%	DIN 53504
Elastomers	Nominal Value	Unit	Test Method
Tear Strength - Flow	75	kN/m	DIN 53515
Injection	Nominal Value	Unit	
Drying Temperature	80 - 100	°C	
Drying Time	2.0 - 4.0	hr	
Processing (Melt) Temp	170	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT