

RTP 1207-80D

Thermoplastic Polyurethane Elastomer (Polyester)

RTP Company

Message:

Warning: The status of this material is 'Commercial: Limited Issue'
The data for this material has not been recently verified.
Please contact RTP Company for current information prior to specifying this grade.

General Information			
Filler / Reinforcement	Glass Fiber,40% Filler by Weight		
Features	Good Abrasion Resistance		
	Good Chemical Resistance		
	Low Temperature Toughness		
RoHS Compliance	Contact Manufacturer		
Appearance	Black		
	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.54	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.20	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.15	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	119		ASTM D785
Durometer Hardness (Shore D)	86		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	8960	MPa	ASTM D638
Tensile Strength (Yield)	131	MPa	ASTM D638
Tensile Elongation (Break)	3.8	%	ASTM D638
Flexural Modulus	6890	MPa	ASTM D790
Flexural Strength (Yield)	172	MPa	ASTM D790
Compressive Strength	89.6	MPa	ASTM D695
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm)	160	J/m	ASTM D256
Unnotched Izod Impact (3.18 mm)	1300	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	138	°C	
1.8 MPa, Unannealed	93.3	°C	

CLTE - Flow	2.7E-5	cm/cm/°C	ASTM D696
Thermal Conductivity	0.43	W/m/K	ASTM C177
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+11	ohms·cm	ASTM D257
Dielectric Strength	18	kV/mm	ASTM D149
Dielectric Constant (1 MHz)	4.20		ASTM D150
Dissipation Factor (1 MHz)	0.017		ASTM D150
Arc Resistance	90.0	sec	ASTM D495
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Rear Temperature	182 to 199	°C	
Middle Temperature	188 to 204	°C	
Front Temperature	193 to 210	°C	
Mold Temperature	15.6 to 65.6	°C	
Injection Pressure	68.9 to 103	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

