

S&E; Wire & Cable GA-1021-CJ (All Colors)

Polyvinyl Chloride
S&E; Specialty Polymers, LLC

Message:
75° C CMR, CL2R, AND FPLR flame retardant jacketing compound.

General Information			
Additive	Flame Retardant		
Features	Flame Retardant		
Uses	Wire & Cable Applications		
Wire Types	CL2R		
	CMR		
	FPLR		
Appearance	Colors Available		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.39 to 1.43	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A	97		
Shore A, 3 sec	91 to 97		
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	20.7	MPa	ASTM D412
Tensile Elongation (Break)	290	%	ASTM D412
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-20.0	°C	ASTM D746
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	34	%	ASTM D2863

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT