

Andur 9-AP/Curene® 442

Polyurethane (Polyester, TDI)
Anderson Development Company

Message:
All properties based on Andur® 9-AP cured with Curene® 442

General Information			
Forms	Liquid		
Processing Method	Casting		
Hardness	Nominal Value	Test Method	
Durometer Hardness (Shore A)	90	ASTM D2240	
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	46.2	MPa	ASTM D638
Tensile Elongation (Break)	600	%	ASTM D638
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
100% strain	5.52	MPa	ASTM D412
300% strain	18.6	MPa	ASTM D412
Tear Strength ¹	101	kN/m	ASTM D624
Compression Set	28	%	ASTM D395
Thermoset	Nominal Value	Unit	
Pot Life	7.0 - 8.0	min	
Demold Time	30 - 40	min	
Additional Information			
Hardness, Shore A: 90-92Curene® 442 Temperature, °F: 240-250Prepolymer Temperature, °F: 212-220			
NOTE			
1.	C mould		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT