

RTP ESD C 2800 B-65A Black

Thermoplastic Vulcanizate

RTP Company

Message:

Electrically Conductive - ESD Protection

General Information			
Features	Electrically Conductive		
	ESD Protection		
RoHS Compliance	Contact Manufacturer		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.02	g/cm ³	ASTM D792
Moisture Content	0.030	%	
Static Decay ¹	< 2.0	sec	FTMS 101C 4046.1
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 10 sec)	65		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ² (100% Strain, 3.18 mm)	2.59	MPa	ASTM D412
Tensile Strength ³ (Break, 3.20 mm)	7.24	MPa	ASTM D412
Tensile Elongation ⁴ (Break)	450	%	ASTM D412
Tear Strength ⁵	32.4	kN/m	ASTM D624
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	< 1.0E+5	ohms	ASTM D257
Volume Resistivity	< 1.0E+3	ohms · cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.50 mm, ** Values per RTP Company testing.)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	79.4	°C	
Drying Time	2.0	hr	
Dew Point	-17.8	°C	
Processing (Melt) Temp	182 to 210	°C	
Mold Temperature	15.6 to 65.6	°C	
Injection Pressure	82.7 to 124	MPa	
NOTE			
1.	MIL-PRF-81705D, 5kV to 50 V, 12% RH		
2.	Die C, 510 mm/min		
3.	Die C, 500 mm/min		

4.	Die C, 500 mm/min
5.	Die C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

