

TechnoFiber PP LGF30 -10 HI

Polypropylene
TechnoCompound GmbH

Message:

TechnoFiber PP LGF30 -10 HI is a Polypropylene material filled with 30% long glass fiber. It is available in Europe for injection molding.

General Information			
Filler / Reinforcement	Long Glass Fiber,30% Filler by Weight		
Appearance	Black		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.12	g/cm ³	ISO 1183
Ash Content (625°C)	30	%	ISO 3451
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	7000	MPa	ISO 527-2
Tensile Strain (Break)	2.6	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	18	kJ/m ²	
23°C	25	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	50	kJ/m ²	
23°C	60	kJ/m ²	
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	2.0 to 4.0	hr	
Processing (Melt) Temp	230 to 280	°C	
Mold Temperature	60.0 to 80.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT