

Miramid® VE35CW

Polyamide 6

BASF Leuna GmbH

Message:

Miramid® VE35CW is a Polyamide 6 (Nylon 6) material filled with 35% glass fiber. It is available in Europe for injection molding.

Important attributes of Miramid® VE35CW are:

Chemical Resistant

Crystalline

Fast Molding Cycle

Good Stiffness

Heat Stabilizer

Typical applications include:

Engineering/Industrial Parts

Automotive

Construction Applications

Electrical/Electronic Applications

Sporting Goods

General Information	
Filler / Reinforcement	Glass Fiber,35% Filler by Weight
Additive	Heat Stabilizer
	Mold Release
Features	Crystalline
	Fast Molding Cycle
	Fuel Resistant
	Good Flow
	Good Stability
	Good Stiffness
	Grease Resistant
	Heat Stabilized
	High Rigidity
	Oil Resistant
	Solvent Resistant
Uses	Automotive Applications
	Building Materials
	Electrical/Electronic Applications
	Engineering Parts
	Machine/Mechanical Parts
	Sporting Goods
Forms	Granules
Processing Method	Injection Molding

Multi-Point Data		Isothermal Stress vs. Strain (ISO 11403-1)		
		Secant Modulus vs. Strain (ISO 11403-1)		
		Shear Modulus vs. Temperature (ISO 11403-1)		
Physical	Dry	Conditioned	Unit	Test Method
Density	1410	--	kg/m ³	ISO 1183 ¹
Water Absorption				ISO 62 ²
Saturation	5.5	--	%	
Equilibrium	1.6	--	%	
Viscosity number	145	--	cm ³ /g	ISO 307, 1157, 1628 ³
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile modulus	10000	7000	MPa	ISO 527-2 ⁴
Tensile Stress (Break)	180	115	MPa	ISO 527-2 ⁵
Tensile Strain (Break)	3.0	6.0	%	ISO 527-2 ⁶
Flexural Stress ⁷	280	160	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy notched impact strength				ISO 179/1eA ⁸
-30°C	12.0	--	kJ/m ²	
23°C	14.0	23.0	kJ/m ²	
Charpy impact strength				ISO 179/1eU ⁹
-30°C	60.0	--	kJ/m ²	
23°C	90.0	100	kJ/m ²	
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				ISO 75-2 ¹⁰
0.45 MPa	215	--	°C	
1.8 MPa	205	--	°C	
Melting Temperature (DSC)	220	--	°C	ISO 3146
Electrical	Dry	Conditioned	Unit	Test Method
Volume resistivity	1.0E+13	1.0E+10	ohms·m	IEC 60093 ¹¹
Dielectric Constant (1 MHz)	3.60	6.00		IEC 60250
Dissipation Factor (1 MHz)	0.020	0.20		IEC 60250 ¹²
Comparative tracking index	500	--		IEC 60112 ¹³
Injection	Dry	Unit		
Processing (Melt) Temp	260 to 290		°C	
Mold Temperature	80.0 to 120		°C	
NOTE				
1.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.			
2.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.			

3.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
4.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
5.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
6.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
7.	Typical values for uncoloured product at 23°C
8.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
9.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
10.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
11.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
12.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
13.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT