

Crastin® S600F40 NC010

THERMOPLASTIC POLYESTER RESIN

DuPont Performance Polymers

Message:

Unreinforced Low Viscosity Polybutylene Terephthalate

General Information			
UL YellowCard	E41938-257809		
Additive	Mold Release		
Agency Ratings	UL Unspecified Rating		
Forms	Pellets		
Processing Method	Injection Molding		
Multi-Point Data	Isothermal Stress vs. Strain (ISO 11403-1)		
	Secant Modulus vs. Strain (ISO 11403-1)		
	Shear Stress vs. Shear Rate (ISO 11403-1)		
	Viscosity vs. Shear Rate (ISO 11403-2)		
Part Marking Code (ISO 11469)	>PBT<		
Resin ID (ISO 1043)	PBT		
Physical	Nominal Value	Unit	Test Method
Density	1.31	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (250°C/2.16 kg)	33	g/10 min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	1.8	%	
Flow	1.9	%	
Water Absorption			ISO 62
23°C, 24 hr, 2.00 mm	0.40	%	
Equilibrium, 23°C, 2.00 mm, 50% RH	0.20	%	
Viscosity Number	120	cm³/g	ISO 307
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2600	MPa	ISO 527-2
Tensile Stress (Yield)	58.0	MPa	ISO 527-2
Tensile Strain (Yield)	6.0	%	ISO 527-2
Nominal Tensile Strain at Break	30	%	ISO 527-2
Tensile Creep Modulus			ISO 899-1
1 hr	2600	MPa	
1000 hr	1800	MPa	
Flexural Modulus	2400	MPa	ISO 178
Flexural Stress	85.0	MPa	ISO 178

Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	4.0	kJ/m ²	
23°C	4.0	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	No Break		
23°C	No Break		
Notched Izod Impact Strength (23°C)	4.0	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	115	°C	ISO 75-2/B
0.45 MPa, Annealed	180	°C	ISO 75-2/B
1.8 MPa, Unannealed	50.0	°C	ISO 75-2/A
1.8 MPa, Annealed	60.0	°C	ISO 75-2/A
Glass Transition Temperature ¹	55.0	°C	ISO 11357-2
Vicat Softening Temperature	175	°C	ISO 306/B50
Melting Temperature ²	225	°C	ISO 11357-3
CLTE			ISO 11359-2
Flow	1.1E-4	cm/cm/°C	
Transverse	1.2E-4	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	> 1.0E+15	ohms · cm	IEC 60093
Electric Strength	26	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
100 Hz	3.80		
1 MHz	3.20		
Dissipation Factor			IEC 60250
100 Hz	2.0E-3		
1 MHz	0.020		
Comparative Tracking Index	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flammability Classification			IEC 60695-11-10, -20
0.800 mm	HB		
1.50 mm	HB		
Oxygen Index	22	%	ISO 4589-2
Fill Analysis	Nominal Value	Unit	
Melt Density	1.11	g/cm ³	
Specific Heat Capacity of Melt	2110	J/kg/°C	
Thermal Conductivity of Melt	0.21	W/m/K	
NOTE			
1.	10°C/min		
2.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

