

Envir® PA66T2HL-BK0603

Polyamide 66

Barnet

Message:

Envir® PA66T2HL-BK0603 is a highly Toughened Nylon 66 molding resin, it is Heat stabilized and Lubricated for high performance and processing. 66T2HL offers a versatile balance of strength and toughness, it is provided Black in color.

General Information			
Additive	Heat Stabilizer Lubricant		
Features	Balanced Stiffness/Toughness Good Processability Heat Stabilized Lubricated		
Appearance	Black		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.11	g/cm ³	ASTM D792
Melt Volume-Flow Rate (MVR) (275°C/5.0 kg)	30.0	cm ³ /10min	ASTM D1238
Moisture Content	< 0.20	%	ASTM D6980
Granularity	1.50	g/100 pellets	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2580	MPa	ISO 527-2
Tensile Stress			ISO 527-2
Yield	60.0	MPa	
Break	50.0	MPa	
Tensile Strain			ISO 527-2
Yield	4.3	%	
Break	28	%	
Flexural Modulus	2380	MPa	ISO 178
Flexural Stress	92.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (23°C)	18	kJ/m ²	ISO 180/A
Thermal	Nominal Value	Unit	Test Method
Peak Melting Temperature	260	°C	ASTM D3418

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

