

Axiall PVC 15642

Flexible Polyvinyl Chloride

Axiall Corporation

Message:

Non-lead stabilized semi-rigid insulation compound recommended for Style #1061 applications. Maximum service temperature of 105C.

General Information			
Uses	Insulation		
Wire Types	UL Style 1061		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.34	g/cm³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	60		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
--	22.1	MPa	
100% Strain	20.0	MPa	
Tensile Elongation (Break)	300	%	ASTM D638
Aging	Nominal Value	Unit	Test Method
Retention of Tensile Elongation - Air Aging, 7 days (136°C, 762.0 µm)	88	%	UL 1581
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-8.00	°C	ASTM D746
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity (23°C)	1.0E+15	ohms·cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	28	%	ASTM D2863
Extrusion	Nominal Value	Unit	
Melt Temperature	188	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT