

Karina BLACK PVC COMPOUND -E CAK 85-48/

1

Polyvinyl Chloride

Karina Ind. e Com. de Plásticos Ltda

Message:

RECLAIMED PVC COMPOUND RECOMMENDED FOR SOLES INJECTION.

| General Information | | | |
|--------------------------------------|-------------------|-------------------|-------------|
| Recycled Content | Yes | | |
| Uses | Footwear | | |
| Appearance | Black | | |
| Processing Method | Injection Molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.43 to 1.49 | g/cm ³ | ASTM D792 |
| Color | OK | | ME 12 |
| Abrasion Resistance | < 270 | mm ³ | DIN 53516 |
| Tear Resistance | > 55.0 | kN/m | DIN 53507 |
| Hardness | Nominal Value | Unit | Test Method |
| Durometer Hardness (Shore A, 15 sec) | 83 to 87 | | ASTM D2240 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength | > 11.8 | MPa | ASTM D638 |
| Tensile Elongation (Yield) | > 200 | % | ASTM D638 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

