

VITAMIDE® BR38BK9023

Polyamide 6
Jackdaw Polymers

Message:

VITAMIDE® BR38BK9023 is a Polyamide 6 (Nylon 6) product filled with 40% glass fiber. It is available in Europe. Primary characteristic: flame rated.

General Information			
Filler / Reinforcement	Glass Fiber,40% Filler by Weight		
Appearance	Black		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.46	g/cm ³	ASTM D792, ISO 1183
Water Absorption (23°C, 24 hr)	1.4	%	ASTM D570, ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	200	MPa	ASTM D638, ISO 527-2
Tensile Elongation (Break)	2.0	%	ASTM D638, ISO 527-2
Flexural Modulus	10000	MPa	ASTM D790, ISO 178
Flexural Stress			
--	225	MPa	ISO 178
Break	225	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	14	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength	60	kJ/m ²	ISO 179
Notched Izod Impact Strength	17	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	215	°C	ASTM D648, ISO 75-2/B
1.8 MPa, Unannealed	205	°C	ASTM D648, ISO 75-2/A
Peak Melting Temperature	218	°C	ASTM D2117, ISO 1218
CLTE - Flow	3.2E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms · cm	ASTM D257, IEC 60093
Dielectric Strength	35	kV/mm	ASTM D149, IEC 60243-1
Comparative Tracking Index (Solution A)	550	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Oxygen Index	22	%	ASTM D2863, ISO 4589-2

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

