# NEOPLAST 180 FT EB

### Thermoplastic Vulcanizate

## Zylog Plastalloys

#### Message:

Neoplast 180 FT EB is a soft, dynamically vulcanized thermoplastic vulcanizate (TPV), based on polyolefin chemistry, and is intended for Injection Moulding, Blow Moulding and Extrusion applications.

Key Features:

Excellent Ozone resistance, Good Flex fatigue, RoHS Compliant, UV Stabilised

General Information	
Additive	UV Stabilizer
Features	Fatigue Resistant
	Good UV Resistance
	Ozone Resistant
	Soft
RoHS Compliance	RoHS Compliant
Processing Method	Blow Molding
	Extrusion
	Injection Molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.960	g/cm³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 5 sec, 23°C)	82		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress <sup>1</sup> (100% Strain)	7.35	MPa	ASTM D412
Tensile Strength <sup>2</sup> (Break)	10.8	MPa	ASTM D412
Tensile Elongation <sup>3</sup> (Break)	550	%	ASTM D412
Tear Strength <sup>4</sup>	39.2	kN/m	ASTM D624
Compression Set (70°C, 22 hr)	45	%	ASTM D395B
Aging	Nominal Value	Unit	Test Method
Aging Change in Tensile Strength in Air (150°C, 168 hr)	Nominal Value	Unit %	Test Method ASTM D573
Change in Tensile Strength in Air (150°C,			
Change in Tensile Strength in Air (150°C, 168 hr) Change in Ultimate Elongation in Air	10	%	ASTM D573
Change in Tensile Strength in Air (150°C, 168 hr) Change in Ultimate Elongation in Air (150°C, 168 hr) Change in Durometer Hardness in Air	-10	%	ASTM D573 ASTM D573
Change in Tensile Strength in Air (150°C, 168 hr) Change in Ultimate Elongation in Air (150°C, 168 hr) Change in Durometer Hardness in Air (150°C, 168 hr)	10 -10 1.0	%	ASTM D573 ASTM D573 ASTM D573
Change in Tensile Strength in Air (150°C, 168 hr) Change in Ultimate Elongation in Air (150°C, 168 hr) Change in Durometer Hardness in Air (150°C, 168 hr) Thermal	10 -10 1.0 Nominal Value	% % Unit	ASTM D573 ASTM D573 ASTM D573 Test Method

1.	500 mm/min
2.	500 mm/min
3.	500 mm/min
4.	500 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

