

LEXAN™ FXD104R resin

Polycarbonate

SABIC Innovative Plastics

Message:

FXD104R is a Light Diffusion effect, which is part of the VisualFX family. Color Package may affect properties.

General Information			
UL YellowCard	E121562-220863		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (200°C/3.8 kg)	7.0	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR) (220°C/5.0 kg)	6.00	cm ³ /10min	ISO 1133
Molding Shrinkage - Flow (3.20 mm)	0.50 to 0.70	%	Internal Method
Water Absorption			ISO 62
Saturation, 23°C	0.35	%	
Equilibrium, 23°C, 50% RH	0.15	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2300	MPa	ASTM D638
--	2350	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	62.0	MPa	ASTM D638
Yield	63.0	MPa	ISO 527-2/50
Break ³	69.0	MPa	ASTM D638
Break	70.0	MPa	ISO 527-2/50
Tensile Elongation			
Yield ⁴	7.0	%	ASTM D638
Yield	6.0	%	ISO 527-2/50
Break ⁵	120	%	ASTM D638
Break	120	%	ISO 527-2/50
Flexural Modulus			
50.0 mm Span ⁶	2370	MPa	ASTM D790
-- ⁷	2300	MPa	ISO 178
Flexural Stress			
--	90.0	MPa	ISO 178
Yield, 50.0 mm Span ⁸	94.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁹			ISO 179/1eA

-30°C	15	kJ/m ²	
23°C	75	kJ/m ²	
Charpy Unnotched Impact Strength ¹⁰			ISO 179/1eU
-30°C	No Break		
23°C	No Break		
Notched Izod Impact			
-30°C	140	J/m	ASTM D256
23°C	900	J/m	ASTM D256
-30°C ¹¹	12	kJ/m ²	ISO 180/1A
23°C ¹²	70	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength ¹³			ISO 180/1U
-30°C	No Break		
23°C	No Break		
Instrumented Dart Impact (23°C, Total Energy)		J	ASTM D3763
63.0			
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, Unannealed, 3.20 mm	126	°C	ASTM D648
1.8 MPa, Unannealed, 100 mm Span ¹⁴	127	°C	ISO 75-2/Ae
Vicat Softening Temperature			
--	154	°C	ASTM D1525 ¹⁵
--	144	°C	ISO 306/B50
--	145	°C	ISO 306/B120
CLTE			
Flow : -40 to 40°C	7.0E-5	cm/cm/°C	ASTM E831
Flow : -40 to 40°C	7.1E-5	cm/cm/°C	ISO 11359-2
Transverse : -40 to 40°C	7.0E-5	cm/cm/°C	ASTM E831
Transverse : -40 to 40°C	7.2E-5	cm/cm/°C	ISO 11359-2
Injection	Nominal Value	Unit	
Drying Temperature	120	°C	
Drying Time	2.0 to 4.0	hr	
Suggested Max Moisture	0.020	%	
Hopper Temperature	60.0 to 80.0	°C	
Rear Temperature	270 to 300	°C	
Middle Temperature	280 to 310	°C	
Front Temperature	290 to 320	°C	
Nozzle Temperature	280 to 310	°C	
Processing (Melt) Temp	290 to 320	°C	
Mold Temperature	80.0 to 120	°C	
NOTE			
1.	5.0 mm/min		
2.	Type I, 50 mm/min		

3.	Type I, 50 mm/min
4.	Type I, 50 mm/min
5.	Type I, 50 mm/min
6.	1.3 mm/min
7.	2.0 mm/min
8.	1.3 mm/min
9.	80*10*3 sp=62mm
10.	80*10*3 sp=62mm
11.	80*10*3
12.	80*10*3
13.	80*10*3
14.	120*10*4 mm
15.	Rate B (120°C/h), Loading 2 (50 N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

