

VITAMIDE® AI13BK8503

Polyamide 66

Jackdaw Polymers

Message:

VITAMIDE® AI13BK8503 is a Polyamide 66 (Nylon 66) product. It is available in Europe.

Characteristics include:

Flame Rated

Impact Modified

General Information			
Additive	Impact Modifier		
Features	Impact Modified		
Appearance	Black		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.10	g/cm ³	ASTM D792, ISO 1183
Water Absorption (23°C, 24 hr)	1.2	%	ASTM D570, ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	60.0	MPa	ASTM D638, ISO 527-2
Tensile Elongation (Break)	40	%	ASTM D638, ISO 527-2
Flexural Modulus	2000	MPa	ASTM D790, ISO 178
Flexural Stress			
--	100	MPa	ISO 178
Break	100	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength	30	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	180	°C	ASTM D648, ISO 75-2/B
1.8 MPa, Unannealed	60.0	°C	ASTM D648, ISO 75-2/A
Peak Melting Temperature	255	°C	ASTM D2117, ISO 1218
CLTE - Flow	7.0E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms · cm	ASTM D257, IEC 60093
Dielectric Strength	31	kV/mm	ASTM D149, IEC 60243-1
Comparative Tracking Index (Solution A)	450	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

