

Axiall PVC 1754 Clear 7002

Flexible Polyvinyl Chloride

Axiall Corporation

Message:

Flexible polyvinyl chloride compound formulated for CFR 21 applications. The compound possesses exceptional clarity.

General Information			
Features	Food Contact Acceptable		
	High Clarity		
Uses	Food Service Applications		
Agency Ratings	FDA Unspecified Rating		
Appearance	Clear/Transparent		
Processing Method	Wire & Cable Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20 to 1.24	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (175°C/14.9 kg)	26	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, 3 sec)	75		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus - 100% Secant	7.93	MPa	ASTM D638
Tensile Strength	19.0	MPa	ASTM D638
Tensile Elongation (Break)	400	%	ASTM D638
Extrusion	Nominal Value	Unit	
Melt Temperature	174	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT