

Karina BLACK PVC COMPOUND 809D48/ 1-C-IS-AS-LMP

Polyvinyl Chloride

Karina Ind. e Com. de Plásticos Ltda

Message:

Karina BLACK PVC COMPOUND 809D48/ 1-C-IS-AS-LMP is a Polyvinyl Chloride product. It is available in Latin America.

General Information			
Appearance	Black		
Physical	Nominal Value	Unit	Test Method
Specific Gravity ¹	1.33 to 1.39	g/cm ³	ASTM D792
Cadmium Content	< 50	ppm	ASTM D1971
Chromium Content	< 100	ppm	ASTM D1971
Color	OK		ME 12
Color a	-0.820 to 0.780		ME 12
Color b	-0.880 to 0.720		ME 12
Color L	25.5 to 27.1		ME 12
Mercury Content	< 100	ppm	ASTM D1971
Bromine Content	< 100	ppm	IEC 62321
Lead Content	< 100	ppm	ASTM D1971
Maximum Variation of Elongation	< 20	%	UL 83
Maximum Variation of Tensile Strength	< 20	%	UL 83
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	80 to 84		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	> 13.7	MPa	ASTM D638
Tensile Elongation (Yield)	> 300	%	ASTM D638
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength ²	> 13.7	MPa	UL 83
Tensile Elongation ³ (Break)	> 250	%	UL 83
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	< -40.0	°C	ASTM D746
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity ⁴	> 1.0E+13	ohms·cm	ASTM D257
NOTE			
1.	24 hr		
2.	Aged in Air for 168 hr at 100°C		
3.	Aged in Air for 168 hr at 100°C		
4.	24 hr		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

