

Next Nylon 66 Prime Series PG30-01GY

Polyamide 66

Next Polymers Ltd.

Message:

Description
PA66 Glass Fiber Reinforced Grey Compound
Product Applications
Generally used in all sector of industries such as Thermoset component, inlet & outlet pipes, valve bodies relay parts , engine mounts etc
Benefits
Offering Excellent combination of thermal and Mechanical properties.

General Information				
Filler / Reinforcement		Glass fiber reinforced material, 30% filler by weight		
Uses		Valve/valve components Piping system		
Agency Ratings		EC 1907/2006 (REACH)		
RoHS Compliance		RoHS compliance		
Appearance		Grey		
Processing Method		Injection molding		
Physical	Dry	Conditioned	Unit	Test Method
Specific Gravity	1.36	--	g/cm ³	ASTM D792
Molding Shrinkage				ASTM D955
Flow	0.27	--	%	ASTM D955
Transverse flow	0.58	--	%	ASTM D955
Water Absorption				ASTM D570
23°C, 24 hr	1.8	--	%	ASTM D570
Saturation ¹	6.1	--	%	ASTM D570
Hardness	Dry	Conditioned	Unit	Test Method
Rockwell Hardness				ASTM D785
Class m	110	--		ASTM D785
Class r	120	--		ASTM D785
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Strength	170	120	MPa	ASTM D638
Tensile Elongation (Break)	4.0	6.0	%	ASTM D638
Flexural Modulus	9000	6200	MPa	ASTM D790
Flexural Strength	250	190	MPa	ASTM D790
Impact	Dry	Conditioned	Unit	Test Method
Notched Izod Impact (23°C)	110	130	J/m	ASTM D256
Thermal	Dry	Conditioned	Unit	Test Method

Deflection Temperature Under Load				ASTM D648
0.45 MPa, not annealed	260	--	°C	ASTM D648
1.8 MPa, not annealed	250	--	°C	ASTM D648
Melting Temperature	262	--	°C	ASTM D2117
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+13	--	ohms	IEC 60093
Volume Resistivity	1.0E+16	1.0E+16	ohms·cm	IEC 60093
Dielectric Strength	28	24	kV/mm	IEC 60243-1
Comparative Tracking Index	600	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (0.800 mm)	HB	--		UL 94
Additional Information				

干燥
This grade is not suitable for food contact, medical devices or toy applications

Injection	Dry	Unit
Drying Temperature - Hot Air Dryer	80.0	°C
Drying Time	4.0 - 6.0	hr
Suggested Max Moisture	0.20	%
Rear Temperature	270 - 280	°C
Middle Temperature	280 - 290	°C
Front Temperature	290 - 300	°C
Mold Temperature	65.0 - 85.0	°C

NOTE

1. Immersed

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China


WECHAT