

VALOX™ VX4920 resin

Polybutylene Terephthalate
SABIC Innovative Plastics Europe

Message:

VALOX VX4920 is a 20% glass reinforced nucleated PBT/ASA blend with excellent mechanical properties, high dimensional stability and low density. Applications: connectors and automotive industry.

General Information			
UL YellowCard	E45329-524769		
Filler / Reinforcement	Glass Fiber,20% Filler by Weight		
Additive	Nucleating Agent		
Features	Good Dimensional Stability		
	Low Density		
	Nucleated		
Uses	Automotive Applications		
	Connectors		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.38	g/cm³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR)			ASTM D1238
200°C/3.8 kg	17	g/10 min	
265°C/5.0 kg	35	g/10 min	
Melt Volume-Flow Rate (MVR)			ISO 1133
250°C/5.0 kg	17.0	cm³/10min	
265°C/5.0 kg	30.0	cm³/10min	
Molding Shrinkage			Internal Method
Flow ¹	0.20 to 0.40	%	
Flow : 3.20 mm	0.30 to 0.60	%	
Across Flow ²	0.40 to 0.80	%	
Water Absorption			ISO 62
Saturation, 23°C	0.76	%	
Equilibrium, 23°C, 50% RH	0.27	%	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	118		ISO 2039-2
Ball Indentation Hardness (H 358/30)	130	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			

-- ³	7200	MPa	ASTM D638
--	7200	MPa	ISO 527-2/1
Tensile Strength			
Yield ⁴	90.0	MPa	ASTM D638
Yield	105	MPa	ISO 527-2/5
Break ⁵	105	MPa	ASTM D638
Break	105	MPa	ISO 527-2/5
Tensile Elongation			
Yield ⁶	3.0	%	ASTM D638
Yield	3.0	%	ISO 527-2/5
Break ⁷	3.0	%	ASTM D638
Break	3.0	%	ISO 527-2/5
Flexural Modulus			
50.0 mm Span ⁸	5500	MPa	ASTM D790
-- ⁹	5700	MPa	ISO 178
Flexural Stress			
--	155	MPa	ISO 178
Yield, 50.0 mm Span ¹⁰	135	MPa	ASTM D790
Break, 50.0 mm Span ¹¹	160	MPa	ASTM D790
Taber Abrasion Resistance (1000 Cycles, 1000 g, CS-17 Wheel)	80.0	mg	Internal Method
Flexural Strain at Break ¹²	4.0	%	ISO 178
Filler Content	20	%	ASTM D229
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			
-30°C ¹³	5.0	kJ/m ²	ISO 179/1eA
-30°C	8.0	kJ/m ²	ISO 179/2C
23°C ¹⁴	6.0	kJ/m ²	ISO 179/1eA
23°C	10	kJ/m ²	ISO 179/2C
Charpy Unnotched Impact Strength			
-30°C ¹⁵	40	kJ/m ²	ISO 179/1eU, ISO 179/2U
23°C ¹⁶	45	kJ/m ²	ISO 179/1eU
23°C	55	kJ/m ²	ISO 179/2U
Notched Izod Impact			
-30°C	70	J/m	ASTM D256
0°C	75	J/m	ASTM D256
23°C	80	J/m	ASTM D256
-30°C ¹⁷	7.0	kJ/m ²	ISO 180/1A
0°C ¹⁸	7.0	kJ/m ²	ISO 180/1A
23°C ¹⁹	7.0	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
-30°C	610	J/m	ASTM D4812

23°C	680	J/m	ASTM D4812
-30°C ²⁰	40	kJ/m ²	ISO 180/1U
23°C ²¹	45	kJ/m ²	ISO 180/1U
Instrumented Dart Impact (23°C, Total Energy)	50.0	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed, 3.20 mm	210	°C	ASTM D648
0.45 MPa, Unannealed, 100 mm Span ²²	209	°C	ISO 75-2/Be
0.45 MPa, Unannealed, 64.0 mm Span ²³	210	°C	ISO 75-2/Bf
1.8 MPa, Unannealed, 3.20 mm	170	°C	ASTM D648
1.8 MPa, Unannealed, 100 mm Span ²⁴	179	°C	ISO 75-2/Ae
1.8 MPa, Unannealed, 64.0 mm Span ²⁵	170	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	220	°C	ASTM D1525, ISO 306/A50 14 ²⁶
--	170	°C	ASTM D1525, ISO 306/B50 15 ²⁷
--	165	°C	ISO 306/B120
Ball Pressure Test (125°C)	Pass		IEC 60695-10-2
CLTE			
Flow : -40 to 40°C	3.0E-5	cm/cm/°C	ASTM E831
Flow : -40 to 40°C	2.9E-5	cm/cm/°C	ISO 11359-2
Flow : 23 to 60°C	3.0E-5	cm/cm/°C	ISO 11359-2
Flow : 23 to 150°C	2.4E-5	cm/cm/°C	ISO 11359-2
Transverse : -40 to 40°C	1.1E-4	cm/cm/°C	ASTM E831
Transverse : -40 to 40°C	7.7E-5	cm/cm/°C	ISO 11359-2
Transverse : 23 to 60°C	1.1E-4	cm/cm/°C	ISO 11359-2
Transverse : 23 to 150°C	1.6E-4	cm/cm/°C	ISO 11359-2
Thermal Conductivity	0.25	W/m/K	ISO 8302
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	ohms · cm	ASTM D257, IEC 60093
Dielectric Strength			ASTM D149, IEC 60243-1
1.60 mm, in Oil	28	kV/mm	
3.20 mm, in Oil	24	kV/mm	
Dielectric Constant			
1 MHz	3.40		ASTM D150, IEC 60250
50 Hz	3.40		IEC 60250
60 Hz	3.40		IEC 60250
Dissipation Factor			
1 MHz	0.020		ASTM D150, IEC 60250
50 Hz	2.4E-3		IEC 60250

60 Hz	2.4E-3	IEC 60250	
Comparative Tracking Index (CTI)	PLC 1	UL 746	
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm, Testing by SABIC)	HB		UL 94
Glow Wire Flammability Index (1.00 mm)	750	°C	IEC 60695-2-12
Fill Analysis	Nominal Value	Unit	Test Method
Melt Viscosity (260°C, 1500 sec^-1)	175	Pa·s	ISO 11443
Injection	Nominal Value	Unit	
Drying Temperature	110 to 120	°C	
Drying Time	2.0 to 4.0	hr	
Suggested Max Moisture	0.020	%	
Hopper Temperature	40.0 to 60.0	°C	
Rear Temperature	230 to 245	°C	
Middle Temperature	240 to 255	°C	
Front Temperature	245 to 265	°C	
Nozzle Temperature	240 to 260	°C	
Processing (Melt) Temp	250 to 270	°C	
Mold Temperature	40.0 to 100	°C	
NOTE			
1.	Tensile Bar		
2.	Tensile Bar		
3.	5.0 mm/min		
4.	Type I, 5.0 mm/min		
5.	Type I, 5.0 mm/min		
6.	Type I, 5.0 mm/min		
7.	Type I, 5.0 mm/min		
8.	1.3 mm/min		
9.	2.0 mm/min		
10.	1.3 mm/min		
11.	1.3 mm/min		
12.	2 mm/min		
13.	80*10*4 sp=62mm		
14.	80*10*4 sp=62mm		
15.	80*10*4 sp=62mm		
16.	80*10*4 sp=62mm		
17.	80*10*4		
18.	80*10*4		
19.	80*10*4		
20.	80*10*4		
21.	80*10*4		
22.	120*10*4 mm		
23.	80*10*4 mm		

24.	120*10*4 mm
25.	80*10*4 mm
26.	Rate A (50°C/h), Loading 2 (50 N)
27.	Rate B (120°C/h), Loading 2 (50 N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

