

Generic Silicone Rubber, LSR - Silica

Silicone Rubber, LSR

Generic

Message:

This data represents typical values that have been calculated from all products classified as: Generic Silicone Rubber, LSR - Silica
This information is provided for comparative purposes only.

General Information			
Filler / Reinforcement	Silica		
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	0.103 to 5.17	MPa	ASTM D638
Uncured Properties	Nominal Value	Unit	
Density (23°C)	1.07 to 1.26	g/cm³	
Pot Life (23°C)	1400	min	
Cured Properties	Nominal Value	Unit	
Shore Hardness (23°C)	7 to 80		
Tensile Strength (23°C)	2.07 to 9.46	MPa	
Tensile Elongation at Break (23°C)	180 to 1100	%	
Tear Strength (23°C)	5.25 to 45.5	kN/m	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT