

TAROLOY 70

Polycarbonate + PBT

Taro Plast S.p.A.

Message:

TAROLOY 70 is a Polycarbonate + PBT (PC+PBT) product. It can be processed by injection molding and is available in Europe.

Characteristics include:

Flame Rated

Chemical Resistant

Good Dimensional Stability

Impact Resistant

General Information			
Features	Good Chemical Resistance		
	Good Dimensional Stability		
	High Impact Resistance		
Appearance	Colors Available		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.28	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (260°C/5.0 kg)	35	g/10 min	ISO 1133
Molding Shrinkage			Internal Method
Across Flow	1.0 to 1.2	%	
Flow	1.0 to 1.2	%	
Water Absorption			ISO 62
23°C, 24 hr	0.090	%	
Saturation, 23°C	0.45	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2300	MPa	ISO 527-2/1
Tensile Stress			ISO 527-2/50
Yield	60.0	MPa	
Break	55.0	MPa	
Tensile Strain (Break)	> 100	%	ISO 527-2/50
Flexural Modulus ¹	2100	MPa	ISO 178
Flexural Stress ²	95.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	80	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	85.0	°C	ISO 75-2/A
Continuous Use Temperature ³	100	°C	IEC 60216

Vicat Softening Temperature	180	°C	ISO 306/A50
Ball Pressure Test (145°C)	Pass		IEC 60695-10-2
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index (Solution A)	300	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	HB		UL 94
Glow Wire Flammability Index (2.00 mm)	650	°C	IEC 60695-2-12
Injection	Nominal Value	Unit	
Drying Temperature			
--	110	°C	
Pre-heater	110 to 120	°C	
Drying Time			
--	2.0	hr	
Pre-heater	2.0 to 4.0	hr	
Processing (Melt) Temp	240 to 260	°C	
Mold Temperature	80.0 to 110	°C	
Injection Rate	Moderate		
NOTE			
1.	1.0 mm/min		
2.	1.0 mm/min		
3.	20000 hrs		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT