

Cellophane™ 390MSC

Regenerated Cellulose

Innovia Films Ltd.

Message:

Nitrocellulose Coated Films for Permeable and Barrier Packaging Applications

Colored transparent general purpose 2 side nitrocellulose coated, heat sealable, barrier films

Literature reference: A105

General Information			
Features	Barrier Resin		
	Biodegradable		
	General Purpose		
	Heat Sealable		
	High Clarity		
	Renewable Resource Content		
	Semipermeable		
Uses	Film		
	Packaging		
Appearance	Clear/Transparent		
	Unspecified Color		
Forms	Film		
Films	Nominal Value	Unit	Test Method
Seal Initiation Temperature ¹ (27 µm)	65.0 to 95.0	°C	
Oxygen Transmission Rate (Wet) (23°C, 27 µm, 0.0% RH)	3.00	cm³/m²/24 hr	ASTM F1927
Water Vapor Transmission Rate (27 µm, 38°C, 90% RH)	20	g · mm/m²/atm/24 hr	ASTM E96
Film Gauge	27.1	µm	Internal Method
Yield (27.1 µm)	25.7	m²/kg	Internal Method
NOTE			
1.	0.5 sec dwell, 0.069 MN/m²		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

