

BJB Epoxy TC-1568 A/B

Epoxy; Epoxide
BJB Enterprises, Inc.

Message:

TC-1568 A/B is a general-purpose white epoxy surface coat that can be used in conjunction with epoxy resin systems. TC-1568 A/B is noted for its ease of application and its ability to hang on vertical surfaces without sag or runoff.

General Information			
Features	General Purpose		
Uses	Coating Applications		
Appearance	White		
Forms	Paste		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.63	g/cm ³	ASTM D792
Specific Gravity			
Part A	1.726	g/cm ³	
Part B	1.047	g/cm ³	
Work Time (25°C) ¹	30.0 to 35.0	min	
Brookfield Viscosity			
Mixed : 25°C	Semi-paste	cP	
Part A : 25°C	Semi-paste	cP	
Part B : 25°C	2.50	Pa · s	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	90		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus	4340	MPa	ASTM D790
Flexural Strength	44.8	MPa	ASTM D790
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	79.4	°C	
1.8 MPa, Unannealed	73.9	°C	
Thermoset	Nominal Value	Unit	
Thermoset Components			
Part A	Mix Ratio by Weight: 100		
Part B	Mix Ratio by Weight: 8.0		
Shelf Life	52	wk	
NOTE			
1.	100g		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT