

WPP PP PPHFGC-1

Polypropylene Homopolymer
Washington Penn Plastic Co. Inc.

Message:

WPP PP PPHFGC-1 is a Polypropylene Homopolymer (PP Homopolymer) product filled with 10% glass fiber. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America. Typical application: Automotive. Primary characteristic: chemically coupled.

General Information			
Filler / Reinforcement	Glass Fiber,10% Filler by Weight		
Features	Chemically Coupled		
Uses	Automotive Applications		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.968	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.50 to 0.80	%	ASTM D955
Water Absorption (24 hr)	0.050	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A	96		
Shore D	73		
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	49.6	MPa	ASTM D638
Tensile Elongation (Break)	5.0	%	ASTM D638
Flexural Modulus	3240	MPa	ASTM D790
Flexural Strength (Yield)	72.4	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
23°C, 3.18 mm	64	J/m	
23°C, 6.35 mm	32	J/m	
Unnotched Izod Impact			ASTM D256
23°C, 3.18 mm	400	J/m	
23°C, 6.35 mm	360	J/m	
Gardner Impact (23°C)	0.791	J	ASTM D3029
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	141	°C	
1.8 MPa, Unannealed	129	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT