

Reny® 1032H

Polyarylamide

Mitsubishi Engineering-Plastics Corp

Message:

Reny® 1032H is a Polyarylamide (PARA) material filled with 60% glass fiber. It is available in Asia Pacific, Europe, or North America for injection molding. Primary attribute of Reny® 1032H: Flame Rated.

General Information				
UL YellowCard		E41179-231740		
Filler / Reinforcement		Glass Fiber,60% Filler by Weight		
Processing Method		Injection Molding		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.79	--	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (275°C/2.16 kg)	9.4	--	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (275°C/2.16 kg)	5.30	--	cm ³ /10min	ISO 1133
Molding Shrinkage	0.40	--	%	
Water Absorption				ISO 62
Saturation, 23°C	0.11	--	%	
Equilibrium, 23°C, 50% RH	0.90	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	24700	22400	MPa	ISO 527-2
Tensile Stress (Break)	249	204	MPa	ISO 527-2
Tensile Strain (Break)	1.4	1.4	%	ISO 527-2
Flexural Modulus	23200	21600	MPa	ISO 178
Flexural Stress	429	357	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength (23°C)	14	14	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength (23°C)	54	61	kJ/m ²	ISO 179
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	237	232	°C	ISO 75-2/B
1.8 MPa, Unannealed	230	223	°C	ISO 75-2/A
CLTE				ISO 11359-2
Flow	1.0E-5	--	cm/cm/°C	
Transverse	4.0E-5	--	cm/cm/°C	
Electrical	Dry	Conditioned	Unit	Test Method

Surface Resistivity	2.0E+14	8.0E+14	ohms	IEC 60093
Volume Resistivity	2.0E+15	8.0E+14	ohms·cm	IEC 60093
Electric Strength				IEC 60243-1
1.00 mm	26	26	kV/mm	
2.00 mm	20	20	kV/mm	
Relative Permittivity				IEC 60250
100 Hz	--	6.00		
1 MHz	--	5.00		
Dissipation Factor				IEC 60250
100 Hz	--	0.020		
1 MHz	--	0.013		
Comparative Tracking Index	550	> 600	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (1.60 mm)	HB	--		UL 94
Injection	Dry	Unit		
Drying Temperature				
A	120		°C	
B	80.0		°C	
Drying Time				
A	> 3.0		hr	
B	> 12		hr	
Rear Temperature	270		°C	
Middle Temperature	275		°C	
Front Temperature	280		°C	
Nozzle Temperature	280		°C	
Mold Temperature	120 to 140		°C	
Injection Pressure	20.0 to 150		MPa	
Injection Rate	Moderate-Fast			
Screw Speed	60 to 150		rpm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT