

POLYTROPE® TPP 1026E

Thermoplastic Polyolefin Elastomer

A. Schulman Inc.

Message:

Extrusion TPO 13% Talc

General Information			
Filler / Reinforcement	Talc,13% Filler by Weight		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.00	g/cm ³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield)	28.0	MPa	ASTM D638
Flexural Modulus ²	2000	MPa	ASTM D790
Additional Information	Nominal Value	Unit	Test Method
Filler Content	13	%	ASTM D5630
NOTE			
1.	50 mm/min		
2.	1.3 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

