

# ChronoFlex® AL 75D

Thermoplastic Polyurethane Elastomer (PC Based)

AdvanSource Biomaterials Corp.

Message:

ChronoFlex AL is a family of biodurable aliphatic polycarbonate-based thermoplastic urethanes designed to overcome surface degradation such as stress-induced microfissures.

With a long history of reliable performance in both long and short term devices, this medical grade polymer has the versatility to be used across a broad range of applicational areas ranging from oncology and neurology to cardiovascular disease management.

These ether-free polyurethane elastomers are biostable and display a low modulus of elasticity, excellent solvent resistance and limited softening in-vivo. These products are adaptable to most standard manufacturing processes and are available in hardnesses ranging from 75 Shore A to 75 Shore D. AdvanSource Biomaterials synthesizes and manufactures medical grade materials offering the ability to tailor physical and mechanical characteristics to support and enhance your end product design.

These mechanical characteristic's, critical to the design and development of medical devices, can incorporate a wide range of physical and chemical properties while maintaining core characteristics such as biodurability and biocompatibility. In most materials, specialized characteristics such as the addition of colorant agents or antimicrobial properties (where applicable) can be added to the polymer to provide a homogenous material and limit secondary processing steps.

In addition, radiopaque agents may also be incorporated into the formula to provide additional product enhancements and may contain up to 40%, by weight, of a radiopaque agent thus allowing varied-scale visibility options.

With an expanding range of secondary operations including custom solution development, prototype coating capabilities, and project management services, ASB's expert team of chemists, scientists, engineers and industry professionals assist in every stage of customers' projects, from concept initiation through full-scale manufacture.

General Information			
Features	Aliphatic		
	Biocompatible		
	Good Chemical Resistance		
	Good Strength		
	High ESCR (Stress Crack Resist.)		
	No Animal Derived Components		
Uses	Medical/Healthcare Applications		
Agency Ratings	ISO 10993 Part 10		
	ISO 10993 Part 11		
	ISO 10993 Part 5		
	USP Class VI		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.10 to 1.40	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (205°C/3.26 kg)	2.0 to 26	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	75		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Break	20.7 to 55.2	MPa	

50% Strain	20.7 to 55.2	MPa	
100% Strain	20.7 to 55.2	MPa	
Tensile Elongation (Break)	100 to 300	%	ASTM D638
Injection	Nominal Value	Unit	
Drying Temperature - Desiccant Dryer	71.1 to 93.3	°C	
Drying Time - Desiccant Dryer	3.0 to 4.0	hr	
Dew Point	-40.0	°C	
Suggested Max Moisture	0.050	%	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

