

Nycal™ 2150R13

Polyamide 66
Technical Polymers, LLC

Message:

Nycal™2150R13 is a polyamide 66 (nylon 66) material, which contains a 13% glass fiber reinforced material. This product is available in North America and is processed by injection molding. Nycal™The main characteristics of 2150R13 are: flame retardant/rated flame.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 13% filler by weight		
Appearance	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.23	g/cm³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	117	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	2.5	%	ASTM D638
Flexural Modulus (23°C)	4830	MPa	ASTM D790
Flexural Strength (23°C)	172	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	48	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	257	°C	ASTM D648
1.8 MPa, not annealed	241	°C	ASTM D648
Melting Temperature	260	°C	DSC
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+14	ohms·cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Additional Information			
Tensile Elongation, ASTM D638: 2 to 3%Volum Resistivity, ASTM D257: >1e14 ohm-cm			
Injection	Nominal Value	Unit	
Drying Temperature	73.9 - 79.4	°C	
Drying Time	3.0 - 4.0	hr	
Processing (Melt) Temp	277 - 304	°C	
Mold Temperature	65.6 - 98.9	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT