

Hylex® P1310 L1 HB

Polycarbonate

Entec Polymers

Message:

Polycarbonate, UV Stabilized, Intermediate Flow, Mold Release, Water Clear

General Information			
UL YellowCard	E157012-100832700		
Additive	Mold Release		
	UV Stabilizer		
Features	Medium Flow		
RoHS Compliance	RoHS Compliant		
Appearance	Clear/Transparent		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	10	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.18 mm)	0.50 to 0.70	%	ASTM D955
Water Absorption (24 hr)	0.15	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	72		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	68.9	MPa	ASTM D638
Tensile Elongation (Break)	130	%	ASTM D638
Flexural Modulus	2340	MPa	ASTM D790
Flexural Strength	96.5	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	800	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	139	°C	
1.8 MPa, Unannealed	132	°C	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+17	ohms · cm	ASTM D257
Dielectric Strength	15	kV/mm	ASTM D149
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.50 mm	HB		
3.00 mm	HB		

Optical	Nominal Value	Unit	Test Method
Refractive Index	1.586		ASTM D542
Transmittance	88.0	%	ASTM D1003
Haze	1.0	%	ASTM D1003

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

