

Latilub 37 B01-02S

Polylactic Acid

LATI S.p.A.

Message:

Self-lubricating product based on Bio-Polymer (PLA, PHB, ...).
Silicone.

General Information			
Additive	Silicone Lubricant		
Features	Renewable Resource Content		
	Self Lubricating		
Physical	Nominal Value	Unit	Test Method
Density	1.28	g/cm ³	ISO 1183
Molding Shrinkage ¹			ISO 294-4
Across Flow : 2.00 mm	0.20 to 0.60	%	
Flow : 2.00 mm	0.20 to 0.60	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	2900	MPa	ISO 527-2/1
Tensile Stress			ISO 527-2/5
Yield, 23°C	55.0	MPa	
Break, 23°C	40.0	MPa	
Tensile Strain			ISO 527-2/5
Yield, 23°C	2.5	%	
Break, 23°C	4.5	%	
Coefficient of Friction			ASTM D1894
vs. Itself - Dynamic	0.20		
vs. Itself - Static	0.22		
Wear Factor	650	10 ⁻⁸ mm ³ /N · m	ASTM D3702
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	3.5	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	20	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	50.0	°C	ISO 75-2/B
1.8 MPa, Unannealed	50.0	°C	ISO 75-2/A
Injection	Nominal Value	Unit	Test Method
Drying Temperature	40.0 to 50.0	°C	
Drying Time	6.0	hr	
Processing (Melt) Temp	170 to 190	°C	

Mold Temperature	15.0 to 30.0	°C
Injection Rate	Moderate	
NOTE		
1.	60 MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

