

INVISION™ GX 5135DG5M2C

Thermoplastic Elastomer

A. Schulman Inc.

Message:

Extrusion TPE Styrenic Rubber

General Information			
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	1.12	g/cm³	ISO 1183
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D, 15 sec)	40		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	21.0	MPa	ISO 527-2/500
Tensile Strain (Break)	600	%	ISO 527-2/500
Fill Analysis	Nominal Value	Unit	Test Method
Melt Viscosity (200°C, 243 sec^-1)	145	Pa·s	ASTM D3835

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT