

TEDUR® L 9217-1

Polyphenylene Sulfide

ALBIS PLASTIC GmbH

Message:

TEDUR® L 9217-1 is a Polyphenylene Sulfide (PPS) product filled with 65% glass\mineral. It is available in Asia Pacific, Europe, or North America.

Applications of TEDUR® L 9217-1 include automotive, engineering/industrial parts and lighting applications.

Characteristics include:

- Flame Rated
- REACH Compliant
- RoHS Compliant
- High Stiffness

General Information			
Filler / Reinforcement	Glass\Mineral,65% Filler by Weight		
Features	High Stiffness		
	Hydrolysis Resistant		
Uses	Automotive Applications		
	Lighting Applications		
	Machine/Mechanical Parts		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Physical	Nominal Value	Unit	Test Method
Density	1.97	g/cm³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	19000	MPa	ISO 527-2
Tensile Stress (Break)	140	MPa	ISO 527-2
Tensile Strain (Break)	1.2	%	ISO 527-2
Flexural Modulus	19000	MPa	ISO 178
Flexural Stress	240	MPa	ISO 178
Flexural Strain at Flexural Strength	1.4	%	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	7.0	kJ/m²	ISO 179/1eA
Charpy Unnotched Impact Strength	25	kJ/m²	ISO 179/1eU
Unnotched Izod Impact Strength	25	kJ/m²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	260	°C	ISO 75-2/A
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index	250	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method

Flame Rating (0.750 mm)	V-0	UL 94
Glow Wire Flammability Index (2.00 mm)	960	°C IEC 60695-2-12
Injection	Nominal Value	Unit
Drying Temperature	130 to 140	°C
Drying Time	2.0 to 4.0	hr
Processing (Melt) Temp	320 to 340	°C
Mold Temperature	> 140	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT