

# IDI SMC S52 (Glass Content 22%)

Thermoset, Unspecified

IDI Composites International

Message:

PRODUCT SERIES: S52 SERIES SMC  
PRODUCT DESCRIPTION: DOCKET 90A - ASTM E162 / ASTM E662  
These materials provide low smoke generation and flame spread in accordance with ASTM E162 and E662 standards.

General Information			
Filler / Reinforcement	Glass Fiber,22% Filler by Weight		
Features	Flame Retardant		
	Low Smoke Emission		
Forms	SMC - Sheet Molding Compound		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.83	g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage - Flow	0.090	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.17	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Barcol Hardness	55 to 60		ASTM D2583
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	15300	MPa	ASTM D638
Tensile Strength	63.8	MPa	ASTM D638
Flexural Modulus	10700	MPa	ASTM D790
Flexural Strength	145	MPa	ASTM D790
Compressive Strength	160	MPa	ASTM D695
Impact	Nominal Value	Unit	Test Method
Unnotched Izod Impact	680	J/m	ASTM D4812
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength	17	kV/mm	ASTM D149
Arc Resistance	180	sec	ASTM D495
Flammability	Nominal Value	Unit	Test Method
Flame Spread Index	12.9		ASTM E662
Optical Density			ASTM E662
Flaming @ 1.5 min	0.700		
Flaming @ 4 min	6.90		
Non-Flaming @ 1.5 min	0.00		
Non-Flaming @ 4 min	1.00		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT