

Altuglas® V 920T

Polymethyl Methacrylate Acrylic
Altuglas International of Arkema Inc.

Message:

Altuglas® V 920T is a Polymethyl Methacrylate Acrylic product. It is available in Asia Pacific or Europe. Typical application: Automotive. Primary characteristic: flame rated.

General Information			
UL YellowCard	E106635-218397		
Forms	Granules		
Multi-Point Data	Isothermal Stress vs. Strain (ISO 11403-1)		
	Secant Modulus vs. Strain (ISO 11403-1)		
	Viscosity vs. Shear Rate (ISO 11403-2)		
Physical	Nominal Value	Unit	Test Method
Density	1.18	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)	6.0	g/10 min	ISO 1133
Molding Shrinkage - Flow	0.20 to 0.60	%	ASTM D955
Water Absorption (Equilibrium, 23°C, 50% RH)	0.30	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	96		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, 23°C)	70.0	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	6.0	%	ISO 527-2
Flexural Modulus (23°C)	3300	MPa	ISO 178
Flexural Stress (23°C)	103	MPa	ISO 178
Compressive Stress (23°C)	110	MPa	ISO 604
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	2.0	kJ/m ²	ISO 179/2C
Charpy Unnotched Impact Strength (23°C)	11	kJ/m ²	ISO 179/2U
Notched Izod Impact Strength (23°C)	1.8	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	100	°C	ISO 75-2/B
1.8 MPa, Unannealed	95.0	°C	ISO 75-2/A
Vicat Softening Temperature	103	°C	ISO 306/B
CLTE - Flow (-30 to 23°C)	6.5E-5	cm/cm/°C	ASTM D696
Specific Heat	2090	J/kg/°C	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+14	ohms	ASTM D257

Volume Resistivity	> 1.0E+15	ohms·cm	ASTM D257
Dielectric Strength	20	kV/mm	ASTM D149
Dielectric Constant (60 Hz)	3.70		ASTM D150
Dissipation Factor (1 MHz)	0.040		ASTM D150
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Optical	Nominal Value	Unit	Test Method
Refractive Index ¹	1.490		ISO 489
Transmittance	92.0	%	ASTM D1003
Haze	0.50	%	ASTM D1003
Injection	Nominal Value	Unit	
Drying Temperature	70.0 to 80.0	°C	
Drying Time	2.0 to 4.0	hr	
Processing (Melt) Temp	220 to 230	°C	
Mold Temperature	70.0 to 80.0	°C	
NOTE			

1. Method B

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT