

Spartech Polycom PE4125

High Density (HMW) Polyethylene
Spartech Polycom

Message:

Spartech Polycom PE4125 is a high density (HMW) polyethylene product, which contains 25% talc filler. It can be processed by blow molding, sheet extrusion molding or thermoforming, and is available in North America. Typical application areas are: automotive industry.

Features include:

- high molecular weight
- Good dimensional stability
- Good stiffness
- Impact resistance

General Information	
Filler / Reinforcement	Talc filler, 25% filler by weight
Features	Good dimensional stability
	Rigid, good
	High molecular weight
	Impact resistance, good
Uses	Application in Automobile Field
Appearance	Available colors
Forms	Particle
Processing Method	Blow molding
	Sheet extrusion molding
	Thermoforming

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.15	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	1.7	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	31.0	MPa	ASTM D638
Tensile Elongation			ASTM D638
Yield	10	%	ASTM D638
Fracture	40	%	ASTM D638
Flexural Modulus - Secant	1380	MPa	ASTM D790
Flexural Strength	41.4	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	210	J/m	ASTM D256
Dart Drop Impact			ASTM D3029
-6°C	0.791	J	ASTM D3029
23°C	2.82	J	ASTM D3029
Thermal	Nominal Value	Unit	Test Method

Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	93.3	°C	ASTM D648
1.8 MPa, not annealed	48.9	°C	ASTM D648
Additional Information			

Flexural Modulus, ASTM D790, Tangent: 270000 psi

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

