

TOTAL Polyethylene EVA 1020 VN 5

Ethylene Vinyl Acetate Copolymer

TOTAL Refining & Chemicals

Message:

EVA 1020 VN 5 is made by a high pressure tubular process.
Grade for very flexible films with very high transparency and good mechanical properties.
Application examples: chemicals bags, coextrusion films.

General Information			
Additive	Antioxidation		
Features	Antioxidation		
	Compliance of Food Exposure		
Uses	Films		
	Bags		
Agency Ratings	FDA Food Exposure, Not Rated		
Forms	Particle		
Processing Method	Blow film		
Multi-Point Data	Viscosity vs. Shear Rate (ISO 11403-2)		
Physical	Nominal Value	Unit	Test Method
Density			
--	0.940	g/cm ³	ISO 1183
--	940	kg/m ³	ISO 1183 ¹
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	2.0	g/10 min	ISO 1133
Melt volume-flow rate (190°C/2.16 kg)	2.50	cm ³ /10min	ISO 1133 ²
Vinyl Acetate Content	17.5	wt%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	50.0	MPa	ISO 527-2
Tensile Strain (Yield)	25	%	ISO 527-2 ³
Tensile Elongation at Break	> 50	%	ISO 527-2 ⁴
Films	Nominal Value	Unit	Test Method
Tensile Stress			ISO 527-3
MD: Yield, 40 µm, blown film	5.60	MPa	ISO 527-3
TD: Yield, 40 µm, blown film	4.60	MPa	ISO 527-3
MD: Broken, 40 µm, blown film	29.0	MPa	ISO 527-3
TD: Broken, 40 µm, blown film	28.0	MPa	ISO 527-3
Tensile Elongation			ISO 527-3
MD: Broken, 40 µm, blown film	330	%	ISO 527-3
TD: Broken, 40 µm, blown film	620	%	ISO 527-3

Dart Drop Impact (40 µm, Blown Film)	500	g	ISO 7765-1
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature			
--	64.0	°C	ISO 306
50°C/h, B (50N)	62.0	°C	ISO 306 ⁵
Melting Temperature (DSC)	87.0	°C	ISO 3146
Additional Information			
The value listed as Melting Temperature, ISO 3146, was tested in accordance with ISO 11357. Elmendorf, ISO 6383-2, MD, Blown Film, 40 µm: 26 N/mm Elmendorf, ISO 6383-2, TD, Blown Film, 40 µm: 43 N/mm Haze, ISO 14782, Blown Film, 40 µm: 1.5%			
Extrusion instructions			
Advised Temperature Profile: 150 to 180°C Possible Range of Thicknesses: 20 to 100 µ			
NOTE			

1.	?????,?? ISO 10350 ??? 23°C/50%r.h. ???
2.	?????,?? ISO 10350 ??? 23°C/50%r.h. ???
3.	?????,?? ISO 10350 ??? 23°C/50%r.h. ???
4.	?????,?? ISO 10350 ??? 23°C/50%r.h. ???
5.	?????,?? ISO 10350 ??? 23°C/50%r.h. ???

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT