

LNP™ LUBRICOMP™ RL008 compound

Polyamide 66

SABIC Innovative Plastics Europe

Message:

LNP LUBRICOMP RL008 is a compound based on PA 66 containing PTFE. Added features include: Internally Lubricated.

General Information			
Additive	PTFE Lubricant		
Features	Lubricated		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.42	g/cm ³	ISO 1183
Molding Shrinkage - Flow	2.0	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2300	MPa	ISO 527-2/1
Tensile Stress (Yield)	45.0	MPa	ISO 527-2/5
Tensile Strain (Break)	8.2	%	ISO 527-2/5
Flexural Modulus ¹	2000	MPa	ISO 178
Flexural Stress	67.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength ² (23°C)	4.0	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength ³ (23°C)	30	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ⁴			
0.45 MPa, Unannealed, 64.0 mm Span	207	°C	ISO 75-2/Bf
1.8 MPa, Unannealed, 64.0 mm Span	73.0	°C	ISO 75-2/Af
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.15 to 0.25	%	
Rear Temperature	266 to 277	°C	
Middle Temperature	282 to 293	°C	
Front Temperature	293 to 304	°C	
Processing (Melt) Temp	277 to 288	°C	
Mold Temperature	82.2 to 93.3	°C	
Back Pressure	0.172 to 0.344	MPa	
Screw Speed	30 to 60	rpm	
NOTE			
1.	2.0 mm/min		

2.	80*10*4
3.	80*10*4
4.	80*10*4 mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

