

Spartech Polycom SCR2-1080

High Impact Polystyrene

Spartech Polycom

Message:

Spartech SCR2-1080 is a medium viscosity high impact polystyrene (HIPS) resin for injection molding. It is heat stabilized and lubricated for good processing characteristics.

HIPS are rubber modified styrenics that typically contain 1-10% rubber by weight. They offer dimensional and physical stability in moist environments and provide good chemical resistance. These materials also exhibit good flexibility along with good toughness.

A very versatile product for a wide variety of applications, Spartech SCR2-1080 is recommended for appliance, housewares and electrical/electronic applications.

General Information			
Additive	heat stabilizer		
	Lubricant		
Features	Good dimensional stability		
	Impact resistance, good		
	Workability, good		
	Good flexibility		
	Good chemical resistance		
	Thermal Stability		
	Thermal stability, good		
	Good toughness		
	Lubrication		
	Medium viscosity		
Uses	Electrical/Electronic Applications		
	Electrical appliances		
	Household goods		
Agency Ratings	FDA not rated		
Appearance	Available colors		
	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.04	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR)	9.0	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	20.7	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	50	%	ASTM D638

Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	96	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	86.0	°C	ASTM D648
Injection	Nominal Value	Unit	
Drying Temperature	71.1 - 82.2	°C	
Drying Time	2.0	hr	
Rear Temperature	200 - 220	°C	
Middle Temperature	205 - 225	°C	
Front Temperature	210 - 230	°C	
Nozzle Temperature	210 - 230	°C	
Processing (Melt) Temp	191 - 260	°C	
Mold Temperature	26.7 - 48.9	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

